

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
30 June 2005 (30.06.2005)

PCT

(10) International Publication Number  
**WO 2005/058462 A1**

(51) International Patent Classification<sup>7</sup>: **B01D 53/64**,  
C01B 19/00

(21) International Application Number:  
PCT/FI2004/000768

(22) International Filing Date:  
16 December 2004 (16.12.2004)

(25) Filing Language: Swedish

(26) Publication Language: English

(30) Priority Data:  
0303391-7 17 December 2003 (17.12.2003) SE

(71) Applicant (for all designated States except US): **OUTOKUMPU OYJ** [FI/FI]; Riihitontuntie 7, FIN-02200 Espoo (FI).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **LUNDGREN, Yngve** [SE/SE]; Bladgatan 152, S-931 58 Skellefteå (SE).

(74) Agent: **OUTOKUMPU OYJ, INTELLECTUAL PROPERTY MANAGEMENT**; P.O.Box 27, FIN-02201 Espoo (FI).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Declarations under Rule 4.17:**

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations of inventorship (Rule 4.17(iv)) for US only

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: A METHOD OF RECYCLING AN EXHAUSTED SELENIUM FILTER MASS

(57) Abstract: A process for reclaiming spent selenium filter mass containing an inert material, following take-up of mercury by a substance which contains selenium and is present in the filter mass. The spent mass is treated with a hydrogen peroxide solution for leaching out of the selenium content in essentially all unspent active substance present in the mass to form selenious acid. The resulting selenious acid is separated and isolated for use. The mass freed of the solution is treated with aqua regia for dissolving essentially all of the mercury selenide present in the mass. The aqua regia solution with its content of mercury and selenium are separated from the mass and isolated. Suitably, after it has been washed and dried, the mass freed of the aqua regia solution, which now only contains inert carrier material, and also the previously isolated selenious acid, are transferred to production of new selenium filter mass. After partial neutralisation of the solution, mercury is precipitated in a form that allows it to be deposited. Before that, selenium can be selectively separated and obtained from the aqua regia solution after its pH value has been adjusted, and isolated as elemental selenium useful for the production of new filter mass. Reclaimed selenium content and inert carrier material contained in the filter can advantageously be used for the production of new selenium filters.

WO 2005/058462 A1